



Pilkington **Suncool™** Pro T Coating Range

Benefits:

- High performance solar control toughenable coated glass
- Colour matched to Pilkington **Suncool™** products
- Short lead times in comparison to cut sizes.

Product Data:

Substrates:	Pilkington Optifloat™ Clear & Pilkington Optiwhite™
Thickness:	6 mm, 8 mm, 10 mm & 12 mm
Availability:	Please contact Pilkington Architectural for current lead times
Products:	Double Glazed Units ⁴ Double Glazed Laminates ⁴ Triple Glazed Units ⁴

Frit on Coated Surface:	No	Application:	Surface #2
Size Limitation:	4800 x 2400 mm ¹	Maximum Edge Dip:	0.25 mm
Maximum Bow:	0.15% ³	Mean Roller Wave Depth²:	6 mm – 0.05 mm 8 mm – 0.02 mm 10 mm – 0.02 mm 12 mm – 0.02 mm

Performance Figures:

10mm Outer Pane	16 mm Cavity	6mm Inner Pane	Vtc	Rf(vis)	SHGCc	SCc	U value Summer	U value Winter
Pilkington Suncool™ 70/40 Pro T Clear	Air	Pilkington Optifloat™ Clear	0.68	0.09	0.38	0.44	0.24	0.30
Pilkington Suncool™ 66/33 Pro T Clear	Air	Pilkington Optifloat™ Clear	0.63	0.16	0.32	0.37	0.22	0.29
Pilkington Suncool™ 50/25 Pro T Clear	Air	Pilkington Optifloat™ Clear	0.48	0.18	0.25	0.29	0.22	0.29

10mm Outer Pane	16 mm Cavity	6mm Inner Pane	Vtc	Rf(vis)	SHGCc	SCc	U value Summer	U value Winter
Pilkington Suncool™ 70/40 Pro T Optiwhite™	Air	Pilkington Optiwhite™	0.73	0.10	0.41	0.47	0.24	0.30
Pilkington Suncool™ 66/33 Pro T Optiwhite™	Air	Pilkington Optiwhite™	0.68	0.17	0.34	0.39	0.22	0.29
Pilkington Suncool™ 50/25 Pro T Optiwhite™	Air	Pilkington Optiwhite™	0.52	0.19	0.26	0.30	0.22	0.29

12mm Outer Pane	16 mm Cavity	6mm Inner Pane	Vtc	Rf(vis)	SHGCc	SCc	U value Summer	U value Winter
Pilkington Suncool™ 70/40 Pro T Clear	Air	Pilkington Optifloat™ Clear	0.67	0.09	0.37	0.43	0.24	0.30
Pilkington Suncool™ 66/33 Pro T Clear	Air	Pilkington Optifloat™ Clear	0.62	0.15	0.32	0.37	0.22	0.29
Pilkington Suncool™ 50/25 Pro T Clear	Air	Pilkington Optifloat™ Clear	0.47	0.18	0.25	0.29	0.22	0.29

12mm Outer Pane	16 mm Cavity	6mm Inner Pane	Vtc	Rf(vis)	SHGCc	SCc	U value Summer	U value Winter
Pilkington Suncool™ 70/40 Pro T Optiwhite™	Air	Pilkington Optiwhite™	0.73	0.10	0.41	0.47	0.24	0.30
Pilkington Suncool™ 66/33 Pro T Optiwhite™	Air	Pilkington Optiwhite™	0.68	0.17	0.34	0.39	0.22	0.29
Pilkington Suncool™ 50/25 Pro T Optiwhite™	Air	Pilkington Optiwhite™	0.51	0.19	0.26	0.30	0.22	0.29

Notes:

1. Alternate sizes and combinations possible, please contact Pilkington Architectural for details.
2. Roller wave is usually parallel to the short side and should be glazed horizontally where possible.
3. Refer to particular product specification for maximum bow tolerance on combined glass e.g. laminates etc.
4. The specification of a post-toughenable solar control coating requires that the coating be edge deleted from under the edge seal in order to create a secure and durable hermetic seal. Every effort is made to control the process quality during edge deletion of the coating, however it should be understood that this process can create visible effects at the edge of the unit which can manifest themselves for example as a variation in colour or an apparent metallic sheen running under the edge seal. Such effects are characteristic of the product and do not constitute a reason to reject it.

This publication provides only a general description of the products. Further, more detailed information may be obtained from your local supplier of Pilkington products. It is the responsibility of the user to ensure that the use of these products is appropriate for any particular application and that such use complies with all relevant legislation, standards, code of practice and other requirements. To the fullest extent permitted by applicable laws, Nippon Sheet Glass Co. Ltd. and its subsidiary companies disclaim all liability for any error in or omission from this publication and for all consequences of relying on it.



CE marking confirms that a product complies with its relevant harmonised European Norm.
The CE marking label for each product, including declared values, can be found at www.pilkington.com/CE



Pilkington United Kingdom Ltd.

European Technical Centre, Hall Lane, Lathom, Nr Ormskirk, Lancashire L40 5UF

Telephone 01744 692000 Fax 01744 692880

pilkington@respond.uk.com

www.pilkington.co.uk